


# nastri di acciaio temprabili hardenable steel strips



## Caratteristiche meccaniche Mechanical features

QUALITÀ <i>Quality</i>	EN	R. max N/qmm	A% (LO80) Min.
C45E	10132-3	530	21
C60S	10132-4	550	20
C67S	10132-4	580	20
C75S	10132-4	590	20
C85S	10132-4	620	15
C100S	10132-4	620	15
51CrV4	10132-4	640	18
16MnCr5	10132-2	550	21
25CrMo4	10132-3	580	19
42CrMo4	10132-3	620	15

## Aspetto superficiale Surface finishing

Simbolo <i>Symbol</i>	Finitura <i>Finishing</i>
MA	RL
MB	RL

Valori di rugosità standard  
Standard roughness values  
Ra max 0,6  $\mu\text{m}$   
Ry max 6  $\mu\text{m}$