

# nastri di acciaio temprati hardened & tempered steel strips



qualità  
qualities

Composizione chimica delle principali qualità  
Chemical composition of the most important qualities

QUALITÀ Quality	EN	C %	Mn %	Si %	P %	S %	Cr %	Mo %	Ni %	V %
C60S	10132-4	0.57-0.65	0.60-0.90	0.15-0.35	0.025 Max	0.025 Max	0.40 Max	0.10 Max	0.40 Max	-
C67S	10132-4	0.65-0.73	0.60-0.90	0.15-0.35	0.025 Max	0.025 Max	0.40 Max	0.10 Max	0.40 Max	-
C75S	10132-4	0.70-0.80	0.60-0.90	0.15-0.35	0.025 Max	0.025 Max	0.40 Max	0.10 Max	0.40 Max	-
C85S	10132-4	0.80-0.90	0.40-0.70	0.15-0.35	0.025 Max	0.025 Max	0.40 Max	0.10 Max	0.40 Max	-
C100S	10132-4	0.95-1.05	0.30-0.60	0.15-0.35	0.025 Max	0.025 Max	0.40 Max	0.10 Max	0.40 Max	-
51CrV4	10132-4	0.47-0.55	0.70-1.10	0.40 Max	0.025 Max	0.025 Max	0.90-1.20	0.10 Max	0.40 Max	0.10-0.25
D6A	-	0.42-0.55	0.60-0.90	0.10-0.30	0.030 Max	0.030 Max	0.90-1.20	0.85-1.10	0.40-0.70	0.05-0.25